





CHEM-712: Inorganic and Organometallic Polymers

- Introduction to Inorganic and Organometallic Polymers
- Synthetic Strategies,
- Cyclo and polyphosphazines,
- Cyclo polyphosphazines containing polymers (Introduction, historical, synthesis and applications),
- Phosphorous, Sulphur and Boran containing polymers(Introduction, historical, synthesis, applications and latest developments)
- Polysiloxanes (Introduction, historical, synthesis , applications latest developments latest developments)
- Polysiloxanes and other Silicon containing polymers (Introduction, historical, synthesis, applications & latest developments)

Introduction to Inorganic and Organometallic Polymers

Inorganic polymers are linearly chained large molecules composed of inorganic main chain with inorganic or organic side groups.

[Borazine polymers](#); [Phosphazene polymers](#); [Polysilanes](#); [Polysiloxanes](#); [Silazane polymers](#)



Defining Inorganic Polymers

Various scientists have provided widely differing definitions of inorganic polymers. For example, Currell and Frazer (1) define an inorganic polymer as a macromolecule that does not have a backbone of carbon atoms. In fact, several other reviews define inorganic polymers as polymers that have no carbon atoms in the backbone (2–4). Such definitions leave out almost all coordination and organometallic polymers, even though a sizable number of such polymers have backbone metal atoms that are essential to the stability of the polymer chains.

Organic vs Inorganic Polymers

More Information Online WWW.DIFFERENCEBETWEEN.COM

Organic Polymers

Inorganic Polymers

DEFINITION

Polymer materials that essentially contain carbon atoms in the backbone.

Polymer materials that have no carbon atoms in the backbone.

CARBON ATOMS IN THE BACKBONE

Essentially contain carbon atoms in the backbone

Do not contain carbon atoms in the backbone

STRUCTURE

Most are simple structures

Almost all are highly branched, complex structures

EFFECT ON NATURE

Environmentally friendly as these are biodegradable

Not environmental friendly as these are non-biodegradable

EXAMPLES

Examples include polysaccharides, proteins, polynucleotides, polyesters, etc.

Examples include polydimethylsiloxane (silicone rubber), polyphosphazenes, etc.

Polymers

Polymers are very large molecules made when hundreds of monomers join together to form long chains.

The word 'polymer' comes from the Greek words *poly* (meaning 'many') and *meros* (meaning 'parts').

Example: POLYETHYLENE =
(ETHYLENE+ ETHYLENE+.....)n

Where n = 4,000


DIFFERENT TYPES OF POLYMERS




NATURAL POLYMERS



SYNTHETIC POLYMERS




INORGANIC POLYMERS



ORGANIC POLYMERS

Organic and Inorganic Polymers

A polymer whose backbone chain is essentially made up of carbon atoms is termed as an organic polymer. The atoms attached to side valencies are oxygen, nitrogen, hydrogen etc. Majority of synthetic polymers are organic polymers, for example PE, PVC.



On the other hand, the polymers that do not contain a carbon atom in their backbone chain are called inorganic polymers.






Figure 2. – Polydimethylsiloxane.

Uses

- **Polysiloxane and polyphosphazene elastomers**
- **siloxane and metal-containing**
- **coupling agents,**
- **inorganic dental polymers,**
- **inorganic biomedical polymers,**
- **high temperature lubricants,**
- **preceramic polymers**
- **Conducting and superconducting inorganic polymers for solar energy**
- **nonlinear optics, and paramagnets.**

Introduction Of Inorganic Polymers

- Inorganic polymers by looking its name one can say that they are nonorganic or non-carbon containing polymers. The most obvious definition for an inorganic polymer is a polymers with a skeletal structure that does not include carbon atoms in the backbone.
- Polymer that has inorganic repeating units in their main polymeric backbone are known as inorganic polymers.
- It is a giant 3D or 2D network structure made up by number of covalent bonds but with an absence or near-absence of hydrocarbon units in the main molecular backbone.

Why Do We Need Inorganic Polymers Over Organic Polymers?

- Many organic backbone polymers react with oxygen or ozone over a long period of time and lose their advantageous properties.
- Most organic polymers burn, often with the release of toxic smoke.
- Many organic polymers degrade when exposed to ultraviolet or gamma radiation.
- Organic polymers sometimes soften at unacceptably low temperatures, or they swell or dissolve in organic solvents, oils, or hydraulic fluids.
- Now in case of Inorganic polymers; inorganic elements can have different valencies than carbon, and this means that the number of side groups attached to a backbone may be different from the situation in an organic polymer. This will affect the flexibility of the macromolecule, its ability to react with chemical reagents, its stability at high temperatures, and its interactions with solvents and with other polymer molecules.
- The bonds formed between inorganic elements are often longer, stronger, and more resistant to free radical cleavage reactions than are bonds formed by carbon.

Classification Parameters


- Inorganic polymers represent a rapidly growing field of chemical research and already have many applications and any classification is necessarily somewhat arbitrary.
- N. H. Ray, in his book on inorganic polymers, uses connectivity as a method of classifying inorganic polymers.
- Pittman uses dimensions as a parameter for the classification of inorganic polymers.
- The other classifying parameters are as following:
 1. wholly inorganic polymers
 2. inorganic-organic polymers
 3. organometallic polymers
 4. hybrid organic-inorganic polymers

Classification On The Basis Of Connectivity

- Ray defines connectivity as the number of atoms attached to a defined atom that are a part of the polymer chain or matrix. This polymer connectivity can range from 1 for a side group atom or functional group to at least 8 or 10 in some metal-coordination and metal-cyclopentadienyl polymers, respectively.


Connectivity of 1

- Anchored metal-containing polymers used for catalysis can have connectivity values as low as 1 with respect to the polymer chain as shown in Figure below.




- Note that the metal can have other ligands as well, but in as much as they do not affect the polymer connectivity, the metal is defined as having a connectivity of 1.


Connectivities Of 2




(a) poly-(sulfur nitride)




(b) linear polyphosphate



(c) poly(dichlorophosphazene)




a portion of a silicone chain where R is typically an alkyl organic group



(d)

poly[bis-(R₃phosphine)-μ₂-diacetylenato-C₁, C₄(2-)platinum(II)]




(e)


(e) carborane oligomer with *meta*-B₁₀H₁₀C₂ polyhedra linked by CO (although the hydrogens on the boron atoms and the BH groups in the back of the B₁₀H₁₀C₂ polyhedra are not shown). Carborane polymers with -SiR₂(OSiR₂)_n- linkages also exist

Connectivities of 3


- Such connectivities of 3 provide two-dimensional polymers that are good lubricants and film- and sheet-forming materials



a synthetic silver polymer




boric acid



arsenic(III) sulfide.


Boron in boric oxide has a connectivity of 3, as do the pnictides (N, P, As, Sb, Bi) in some of their binary chalcogenides (e.g., As has a connectivity of 3 in As_2S_3), silicon in silicates such as mica, talc, and pyrophyllite, and carbon in graphite.

Mixed Connectivities of 2 and 3



• Silicon
○ Oxygen


a portion of an asbestos chain.




an ultraphosphoric acid

Connectivities Of 4

- Vitreous silica has silicon atoms with a connectivity of 4. . Boron and aluminium phosphates and many other three-dimensional polymers have connectivities of 4 for at least one type of atom in the polymer




silica with silicon atoms of connectivities of 4




boron phosphate with both phosphorus and boron atoms with connectivities of 4.

Mixed Connectivities of 3 and 4

- A number of polymeric inorganic species have mixed connectivities of 3 and 4, including some borate glasses, where the counter cations provide the counter charges for the four oxide ions connected to at least some of the boron atoms as shown in Figure below.




the boron atoms in a typical borate salt



the silicon atoms in a typical fibrous zeolite.

Connectivities of 6


- Examples of connectivities of 6 include metal coordination polymers having metal atoms or ions joined with two tridentate ligands. A tridentate ligand is a ligand that has three atoms that are coordinated to the same metal atoms or ion.



Examples of connectivities of 6 (or more) for metal atoms/ions

Mixed Connectivities of 4 and 6


- Orthophosphates and arsenates of titanium, zirconium, tin, cerium, thorium, silicon, and germanium have mixed connectivities of 4 and 6. An example is shown below in Figure



An orthophosphate of mixed connectivities of 4 and 6.

Connectivities of 8

- Metal coordination polymers of zirconium(IV), yttrium(III), and several lanthanide ions [cerium(IV), lanthanum(III), europium(III), gadolinium(III), and lutetium(III)] have been synthesized that possess connectivities of 8 because two tetradentate ligands are coordinated to each metal ion that is part of the polymer chain. An example is shown below in Figure.




A Schiff-base polymer of zirconium with a connectivity of 8.

Classifications by dimensionality

- Another manner in which polymers can be classed is by dimensionality. Pittman use this classification for polymeric species containing metal atoms in their backbones. Here we will use the dimensionality for all types of inorganic polymers.
 - i. 1-D Polymeric Structures
 - ii. 2-D Polymeric Structures
 - iii. 3-D Polymeric Structures

1-D Polymeric Structures


- A linear chain polymer is categorized as a one-dimensional (1-D) polymer even though it may have twists and turns in the “linear” chain. Simple polymer chains in which all of the atoms in the chain have a connectivity of 2 are classed as 1-D polymers.
- However, a linear chain polymer with one or more atoms of each repeating unit having a connectivity of more than 2 is also possible. For example, a polymer with benzene rings in the chain will have some carbon atoms with a connectivity of 3.



Schematic metal phosphonate 1-D polymers with connectivities of 2-6.

2-D Polymeric Structures



- Simple inorganic species with a connectivity of 3 often lead to sheet or two dimensional (2-D) polymers as shown in Figure for boric acid & arsenic sulfide.
- On the other hand, connectivities do not always determine illustrate this point, the aqueous iron(II) oxalate polymer has structure, but the analogous 2,5-oxyquinonate complex of its structure as shown below in Figure.






(a)


(b)




(d)



(e)




(c)




(f)

3-D Polymeric Structures

- Inorganic polymeric networks in which bonding occurs in three dimensions are well known. Starting with quartz (SiO_2) as a prime example, the most common characteristic of such species is insolubility — unless decomposition occurs during a dissolution process.
- To have a true 3-D polymer, at least some of the atoms must have a connectivity of 4 or more. Some polymers, such as some of the polysilynes are pseudo-3-D as a result of 3-D ring formation to relieve steric strain.
- Prussian blue is a classic example of a mixed Fe(II) and Fe(III) 3-D polymeric structure, with each iron ion surrounded octahedrally by six cyano ligands.








Prussian blue, a 3-D metal coordination polymeric material.

Classification On The Basis Of Chemical Constituents

- According to this classification method inorganic polymers are classified on the basis of parameters as following:
 1. wholly inorganic polymers
 2. inorganic-organic polymers
 3. organometallic polymers
 4. hybrid organic-inorganic polymers


Inorganic-organic Polymers

- Inorganic polymers containing organic portions attached to inorganic elements in their backbone. The area of inorganic-organic polymers is very extensive. Some examples of this class are: polysilanes, polysiloxanes, polyphosphazenes.



Organometallic Polymers


- Organometallic polymers are made of over 40 elements including main group of metals (si or ge), transition metals or rare earth elements in addition to the 10 elements (C, H, N, O, B, P, halides) which is found in organic polymers. The variations of organometallic polymers seem endless.
- Organometallic polymers are new materials which combine the low density and structural variations and functional group varieties of organic materials with electrical conductivity and the high temperature stability features of inorganic compounds.



Different structures found in organometallic polymers

Hybrid organic-inorganic polymers

- Hybrid organic-inorganic networks, prepared via sol-gel process, are multifunctional materials offering a wide range of interesting properties. Since there are countless different combinations of the organic and inorganic moieties, a large number of applications are possible by incorporation of inorganic building blocks such as silica networks, porous materials and metals.



Π -conjugated polymers prepared via organometallic condensation reactions

